





PA ○ ●

NYLATRON® SLG

Semi-crystalline plastic, NYLATRON® SLG (Self Lubricated Grade), is a self-lubricated polyamide. It has been specially developed for non-lubricated applications whose parts are subjected to high loads and low speeds. Compared with other cast polyamides, it offers more life time, lowering maintenance costs.





MAIN CHARACTERISTICS

- Self-lubricating
- High mechanical resistance, stiffness and hardness
- Good resistance to fatigue
- High mechanical damping capacity
- Good sliding properties
- Excellent resistance to wear
- Good electrical insulation

APPLICATIONS

- Sliding rulers
- In general, all static or dynamic applications requiring lubrication exemption and are subjected to heavy loads and low speeds

POLYLANEMA



*continuously (20.000H)

All figures given are indicative only, Polylanema Lda. is not liable for the use of the materials without consulting with our technical department.



PROPERTIES		TEST METHODS	UNITS	NYLATRON® SLG
COLOR			-	WHITE/BLUE
DENSITY		ISO 1183-1	g/cm³	1.135
WATER ABSORPTION				
AFTER 24/96H IMMERSION IN WATER OF 23°C ¹		ISO 62	mg	44/83
AFTER 24/96H IMMERSION IN WATER OF 23°C ¹		ISO 62	%	0.66/1.24
AT SATURATION IN AIR OF 23°C / 50% RH		-	%	2
AT SATURATION IN WATER OF A 23°C		-	%	6.3
THERMAL PROPERTIES ²				
MELTING TEMPERARUTE (DSC, 10°C/MIN)		ISO 11357-1/-3	°C	215
GLASS TRANSITION TEMPERATURE (DSC, 20°C/MIN) ³		ISO 11357-1/-3	°C	-
THERMAL CONDUCTIVITY A 23°C		-	W/(K.m)	0.28
COEFFICIENT OF LINEAR THERMAL EXPANSION				
AVERAGE VALUE BETWEEN 23-60°C		-	M/(m.K)	80 x 10 ⁻⁶
AVERAGE VALUE BETWEEN 23-100°C		-	M/(m.K)	90 x 10 ⁻⁶
TEMPERATURE OF DEFLECTION UNDER LOAD				
METHOD A 1.8 MPA	+	ISO 75-1/-2	°C	75
MAXIMUM ALLOABLE SERVICE TEMPERATURE IN AIR				
FOR SHORT PERIODS ⁴		-	°C	165
CONTINUOUSLY: FOR 5.000/20.000H ⁵		-	°C	105/90
MINIMUM SERVICE TEMPERATURE ⁶		-	°C	-20
FAMMABILITY ⁷				
"OXYGEN INDEX"		ISO 4589-1/-2	%	-
ACCORDING TO UL94 (3/6MM DE ESPESSURA)		-	-	HB/HB
MECHANICAL PROPERTIES AT 23°C ⁸				
TENSION TEST ⁹				
TENSILE STRESS AT YIELD/AT BREAK ¹⁰	+	ISO 527-1/-2	MPa	72/-
TENSILE STRESS AT YIELD/AT BREAK ¹⁰	++	ISO 527-1/-2	MPa	45/-
TENSILE STRENGTH ¹⁰	+	ISO 527-1/-2	MPa	73
TENSILE STRAIN AT YIELD ¹⁰	+	ISO 527-1/-2	%	5
TENSILE STRAIN AT BREAK ¹⁰	+	ISO 527-1/-2	%	25
TENSILE STRAIN AT BREAK ¹⁰	++	ISO 527-1/-2	%	>50
TENSILE MODULUS OF ELASTICITY ¹¹	+	ISO 527-1/-2	MPa	3000
TENSILE MODULUS OF ELASTICITY ¹¹	++	ISO 527-1/-2	MPa	1450
COMPRESSION TEST ¹²				
COMPRESSIVE STRESS AT 1/2/5% NOMINAL STRAIN ¹¹	+	ISO 604	MPa	31/58/85
CHARPY IMPACT STRENGTH - UNNOTCHED ¹³	+	ISO 179-1/1eU	KJ/m²	50
CHARPY IMPACT STRENGTH - NOTCHED	+	ISO 179-1/1eA	KJ/m²	4
BALL IDENTATION HARDNESS ⁴	+	ISO 2039-1	N/mm²	145
ROCKWELL HARDNESS ¹⁴	+	ISO 2039-2	-	M 82
ELECTRICAL PROPERTIES AT 23°C				
ELECTRIC STRENGTH ¹⁵	+	IEC 60243-1	kV/mm	22
ELECTRIC STRENGTH ¹⁵	++	IEC 60243-1	kV/mm	14
VOLUME RESISTIVITY	+	IEC 60093	Ohm.cm	> 10 ¹⁶
VOLUME RESISTIVITY	++	IEC 60093	Ohm.cm	> 10 ¹²
SURFACE RESISTIVITY	+	IEC 60093	Ohm	> 10 ¹³
SURFACE RESISTIVITY	++	IEC 60093	Ohm	> 10 ¹²
RELATIVE PERMITTIVITY ε _r : A 100HZ	+	IEC 60250	-	3.5
RELATIVE PERMITTIVITY ε _r : A 100HZ	++	IEC 60250	-	6.5
RELATIVE PERMITTIVITY ε _r : A 1MHZ	+	IEC 60250	-	3.1
RELATIVE PERMITTIVITY ε _r : A 1MHZ	++	IEC 60250	-	3.6
DIELECTRIC DISSIPATION FACTOR TAN δ : A 100HZ	+	IEC 60250	-	0.015
DIELECTRIC DISSIPATION FACTOR TAN δ : A 100HZ	++	IEC 60250	-	0.15
DIELECTRIC DISSIPATION FACTOR TAN δ : A 1MHZ	+	IEC 60250	-	0.016
DIELECTRIC DISSIPATION FACTOR TAN δ : A 1MHZ	++	IEC 60250	-	0.05
COMPARATIVE TRACKING INDEX (CTI)	+	IEC 60112	-	600
COMPARATIVE TRACKING INDEX (CTI)	++	IEC 60112	-	600

NOTE: 1 g/cm³ = 1000 kg/m³ ; 1 MPa = 1 N/mm² ; 1 KV/mm = 1 MV/m

+: values for dry material

++: values referring to material in equilibrium with the standard atmosphere 23°C / 50% rh

(1) According to method 1 of ISO 62 and measured on ø 50x3 mm discs. **(2)** The elements supplied for this property are for the most part supplied by the manufacturers of the raw materials. **(3)** The values of this property are only attributed to amorphous rather than semi-crystalline materials. **(4)** Only for short periods of exposure in applications where only very low loads are applied to the material. **(5)** Temperature that resists after a period of 5,000 / 20,000 hours. After this time, there is a decrease of about 50% in tensile strength compared to the original value. The given temperature values are based on the thermal oxidation degradation which occurs which causes a reduction of the properties. In the meantime, the maximum permissible service temperature depends in many cases essentially on the deduction and magnitude of the mechanical stresses to which the material is subject. **(6)** As the impact strength decreases with decreasing temperature, the minimum allowable service temperature is determined by the extent of impact to which the material is subjected. The values given are based on unfavorable impact conditions and can not therefore be considered absolute limits. **(7)** These assessments derive from the technical specifications of the manufacturers of the raw materials and do not allow the determination of the behavior of the materials under fire conditions. **(8)** Most of the figures given by the properties of the (+) materials are mean values of the tests done on species machined with ø 40-60 mm. **(9)** Specimen testing: Type 1b. **(10)** Speed test: 5 or 50 mm / min. **(11)** Speed test: 1m / min. **(12)** Testing specimens: cylinders ø 8 x 16 mm. **(13)** Pendulum used: 15J. **(14)** Test on 10 mm thick specimens. **(15)** Electrode configuration: cylinders ø 25 / ø 75 mm, in transformer oil according to IEC 60296.

Note that the electrical force for the extruded black material can be considerably lower than that of natural material. The possible micro porosity in the center of conserved forms in stock significantly reduces the electric force.